



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : A61F 13/15, 13/46</p>	<p>A1</p>	<p>(11) International Publication Number: WO 98/36721</p> <p>(43) International Publication Date: 27 August 1998 (27.08.98)</p>
<p>(21) International Application Number: PCT/SE98/00292</p> <p>(22) International Filing Date: 19 February 1998 (19.02.98)</p> <p>(30) Priority Data: 9700606-8 21 February 1997 (21.02.97) SE</p> <p>(71) Applicant (for all designated States except US): SCA MÖLNLYCKE AB [SE/SE]; S-405 03 Göteborg (SE).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): JOHANSSON, Anette [SE/SE]; Ernst Kristenssons gata 4A, S-416 58 Göteborg (SE). LJUNGQVIST, Nils [SE/SE]; Hästhagsvägen 4A, 2 tr., S-531 53 Lidköping (SE).</p> <p>(74) Agents: GRAUDUMS, Valdis et al.; Albihns Patentbyrå Göteborg AB, P.O. Box 142, S-401 22 Göteborg (SE).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: LIQUID-PERVIOUS COVER LAYER FOR AN ABSORBENT ARTICLE</p> <div data-bbox="349 1144 1274 1564" data-label="Image"> </div> <p>(57) Abstract</p> <p>The present invention pertains to a liquid-pervious cover layer (1, 201, 301) for an absorbent article, such as a sanitary napkin (300), a panty-liner, a diaper, or the like, which comprises a liquid-pervious carrier layer (2) against which individual hydrophobic fibres (3), detached from each other and each exhibiting two fibre ends, are attached with one fibre end against the carrier layer (2), with an attachment angle α between the carrier layer (2) and each individual fibre (3). The cover layer (1, 201, 301) exhibits fibre-free regions (4) for facilitating liquid transfer through the cover layer. The invention further includes and absorbent article provided with the cover layer (1, 201, 301), and a method of manufacturing the cover layer (1, 201, 301).</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CJ	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

5 LIQUID-PERVIOUS COVER LAYER FOR AN ABSORBENT ARTICLE

TECHNICAL FIELD:

10 The invention pertains to a liquid pervious cover layer for an absorbent article such as a diaper, an incontinence protector, a sanitary napkin or the like, which exhibits a liquid-pervious carrier layer having a first surface and a second surface, wherein the first surface of the carrier layer exhibits a multitude of individually arranged fibres, 15 each fibre exhibiting a first fibre end and a second fibre end, and being attached with one fibre end against the first surface of the carrier layer. The invention also relates to an absorbent article provided with the cover layer and to a method for manufacturing of the cover layer.

20

TECHNICAL BACKGROUND:

High demands on both softness and dryness are made on liquid-pervious cover layers for absorbent articles of this 25 type, which are intended to bear on the body of the user during use.

However, it has proved to be difficult to achieve a liquid-pervious cover layer with a soft and textile-like surface 30 which at the same time remains dry during use.

One problem, when using nonwoven materials or other similar textile materials as liquid-pervious cover layers for absorbent articles, is that the fibre structure of the 35 material absorbs liquid when the cover layer is wetted. A certain amount of the liquid is not conducted downwards to the underlying absorbent structure, but remains in the liquid-pervious cover layer instead. Since the liquid-pervious cover layer bears on the body of the user during

use, such articles are perceived as being wet and uncomfortable to wear already after an initial wetting.

5 Furthermore, the wet surface, which is in direct contact with the skin during use, leads to an increased risk of skin irritations and infections.

10 The most important reason for some of the liquid remaining in the fibre structure is that textile materials usually consist of an irregular fibre structure with fibres or fibre filaments oriented in the plane of the material. This implies that excreted body fluid, by means of the capillary action of the fibres, is distributed along the fibre structure in the direction of the material plane. Also
15 liquid which is not absorbed into the fibre capillaries is conducted along the fibre structure in the direction of the material plane, and is collected in cavities between the fibres in which the liquid is retained without being able to spread further to underlying material. These factors
20 result in a certain amount of liquid remaining in the cover layer and causing a wet surface closest to the user.

Another problem with the nonwoven materials of today, having fibres substantially oriented in parallel with the
25 material plane, is that the possibility to control the wetting course by means of utilizing the properties of the fibres, such as for example the wettability of different fibres, is limited. Furthermore, the possibility to control the wetting course is limited when it comes to the location
30 of the fibres and their design.

It is previously known from US 3,967,623 to use a liquid-pervious cover layer, consisting of a perforated plastic layer, as a carrier material onto which fibres treated with
35 wetting agent are applied in order to create a soft and fluffy surface. The individual fibres are oriented so that

they are directed upwards towards the user during use and are approximately 5 mm long. Since the fibres are directed upwards towards the user, a soft and fluffy surface is created. However, the problem remains that the liquid transfer from the fibres to the underlying absorbent body inside is poor, which results in the surface closest to the user remaining wet after wetting.

BE 09300552 relates to a cover layer for an absorbent article, which cover layer consists of a plastic film which at least on one side is covered by fibres which are attached at an angle to the plastic film. In order to obtain such a structure, the fibres may, for example by means of flocking, be attached with one of their fibre ends against a fused fibre fixation layer on the plastic film. The plastic film may be perforated so that the material becomes liquid-pervious. The fibres are 0.3 to 2.5 mm long and the thickness may be varied with regard to how soft the layer should be. Different fibres may be used, such as for example viscose, cotton, polyethylene, polypropylene, polyester and polyamide.

The risk of the liquid spreading in the plane of the material and thereby along the surface of the cover layer is minimal with this previously known cover layer. Furthermore, the cover layer exhibits a soft surface closest to the user. With this previously known cover layer, however, the problem of achieving a dry surface, when the layer is used as a liquid-pervious surface material on an absorbent article, still remains.

SUMMARY OF THE INVENTION:

By means of the present invention, the problems with achieving a liquid-pervious cover layer for absorbent

articles, which is soft and exhibits a dry surface also after wetting, has essentially been eliminated.

5 Accordingly, by means of the invention, a soft, skin-friendly and textile-like cover layer for an absorbent article has been achieved, which layer has the ability to conduct liquid downwards to an underlying absorbent structure and to thereby maintain a dry surface closest to the user.

10

A liquid-pervious cover layer according to the invention is primarily distinguished by that the carrier layer exhibits a plurality of regions which are substantially free from fibres and which each occupies a surface such that a circle
15 having a diameter of 3 to 15 mm and preferably having a diameter of 3 to 10 mm can be accommodated within each fibre-free region.

The fibre-free regions of the cover layer allow liquid to
20 pass between the hydrophobic fibres, through the liquid pervious cover layer. At the same time, the hydrophobic fibres provide a soft, skin-friendly surface, isolating absorbed liquid from the user's skin when the cover layer is being used as a liquid-pervious topsheet on an absorbent
25 article.

A cover layer in accordance with the invention has been found to perform particularly well when the hydrophobic fibres are 0.3-2.5 mm long and preferably 0.3-1.5 mm long.

30

The fibres can be arranged in a wide variety of different surface patterns such as squares, bands, stars, flowers, dots, rings, etc. Mixed patterns and patterns having varying fibre densities can also be used. When the fibres
35 are arranged in stripes or band-shaped regions, the

distance between two neighbouring fibre-covered regions should be in the order of 3-15 mm and preferably 3-10 mm.

5 In order to achieve the desired liquid-permeability, it has been shown that the total area of the fibre-free regions should occupy at least 25% of the surface of the carrier layer. However, the fibre-free regions should not occupy more than 60% and preferably not more than 50% of the surface.

10 The advantage with such a cover layer is that the hydrophobic surface of the individual fibres creates a dry barrier between the liquid-pervious carrier layer and the user. This implies that the risk that the surface bearing
15 most closely on the user is perceived as wet after wetting is reduced.

According to the invention, the individual fibres are attached only to delimited regions of the total area of the carrier layer, while other regions of the surface of the
20 carrier layer thus are left free from individual fibres. For instance, the individual fibres can be attached in a row pattern along the longitudinal direction of the article. The advantage with such a pattern is that the
25 liquid is distributed from the wetting point in a direction towards the end portions of the article, whereas liquid spreading in the lateral direction is counteracted. Thereby, the risk of the region around the wetting point being saturated with liquid, with leakage in a lateral
30 direction as a consequence, is reduced. A further advantage, with liquid distribution from the wetting point of the article to the end portions of the article, is that the liquid distribution in an underlying absorbent structure becomes more uniform. This results in a better
35 utilization of the total liquid absorption capacity of the underlying structure. The individual fibres may also be

attached in other patterns, wherein the carrier surface exhibits delimited regions which are free from attached fibres.

5 The carrier layer may further exhibit a continuous region across the entire surface of the carrier layer which is free from fibres. This implies that the individual fibres are attached to delimited smaller regions of the surface of the carrier layer, which regions are delimited from each other by the continuous region of the carrier layer which is free from fibres. An advantage with such an embodiment is that the liquid distributing ability of the carrier layer is increased, since the liquid is more easily distributed along a continuous region which is free from attached fibres exhibiting a hydrophobic surface structure. This embodiment is above all advantageous when the carrier layer is constituted of a nonwoven material which in itself can function as a liquid distributing layer, but is of course also applicable for other carrier materials.

20 According to one embodiment, the individual fibres are constituted of bicomponent fibres, exhibiting a hydrophobic surface and a hydrophilic core. An advantage with using such bicomponent fibres is that the hydrophilic core of the fibres has the ability to conduct the liquid downwards towards the liquid-pervious carrier layer. This implies that the liquid quantity between the fibres decreases, resulting in a drier surface and a reduced risk of liquid leakage out to the underpants of the user.

30 According to another embodiment, the components in the bicomponent fibre have different melting temperatures. Thereby, the component which constitutes the core of the fibres preferably exhibits a higher melting temperature than the component which constitutes the outer structure of the fibres. The advantage with a difference in melting

35

temperature is that the need for an adhesive, when attaching the fibres to the carrier layer, is eliminated since the fibres are heated to a temperature between the melting temperatures of the fibre components when they are applied against the carrier material. This implies that the outer component melts, whereby the bicomponent fibres exhibit a melted fibre surface which attaches to the carrier layer.

According to still another embodiment, the individual fibres are constituted of hollow fibres, having an outer surface and an inner surface whereof at least the outer surface of the hollow fibre is hydrophobic. Accordingly, the inner surface of the hollow fibre is either hydrophilic or hydrophobic. An advantage with these fibres is that liquid can be conducted via the cavities of the fibres downwards towards the liquid-pervious carrier layer. This implies that the quantity of external liquid between the individual fibres is reduced, resulting in a drier surface and a reduced risk of liquid leakage to the underpants of the user. A further advantage with hollow fibres is that the material consumption during the manufacture of such fibres is small, which results in a low raw material consumption.

According to still another embodiment, the carrier layer is constituted of a multilayered laminate. The multilayered laminate exhibits at least one bottom layer, and a fibre fixation layer, wherein the fibre fixation layer has a lower melting temperature than the bottom layer. When attaching the individual fibres, the carrier layer is heated to such a temperature that the fibre fixation layer melts, whereas the bottom layer is intact. Accordingly, the need for a special adhesive for attaching the fibres is eliminated.

According to still another embodiment, the carrier layer exhibits liquid-penetrability since the layer has been perforated. This embodiment primarily refers to carrier layers which are constituted of an initially liquid-impervious material, such as a film exhibiting one or several layers, but can also be applied in order to increase the liquid-penetrability of different types of nonwoven materials.

The carrier layer may further comprise a liquid-pervious textile material, such as for example a hydrophilic nonwoven. An advantage with a hydrophilic nonwoven as a carrier material is that such materials are liquid-pervious in themselves. This implies that the carrier layer does not have to be perforated in order to achieve liquid-penetrability. A further advantage with a hydrophilic nonwoven as a carrier material is that such a material has the ability to distribute liquid in the plane of the material layer. Accordingly, such a carrier layer also functions as a liquid distributing layer, which results in a higher degree of utilization of the total absorption capacity of the underlying structure.

In still another embodiment, the fibre density varies across the surface of the carrier layer by using different patterns or pattern densities for different parts of the surface. This implies that the liquid-pervious carrier layer exhibits a difference in the number of attached individual fibres per unit of area. The advantage with a difference in fibre density is that the possibility to guide liquid in the desired direction is increased. A varied fibre density may thus reduce the risk of the region around the wetting point being saturated with liquid with leakage as a consequence.

- According to one embodiment, the attachment angle α , between the carrier layer and each individual fibre is approximately 90°, but may of course vary somewhat between the different fibres. The advantage with such an embodiment is that the body fluid rapidly is conducted in a direction straight into the carrier layer, and further into the underlying absorbent structure. Accordingly, the risk of the layer being perceived as wet is minimized.
- According to another embodiment, the angle α between the carrier layer and each individual fibre is 30-70°. Since the fibres are angled so that they exhibit a smaller angle than 90° between the surface of the carrier layer and the individual fibres, the surface maintains a clean and dry visual impression also after use since the oblique fibres disguise the liquid-pervious carrier layer so that this is not visible when the user observes the sanitary napkin from above.
- There are several factors influencing the choice of fibres and carrier layers, and the location of the fibres across the surface of the carrier layer. For instance, the properties of the material must be adapted with respect to which type of liquid the article is intended to absorb, and to which properties the underlying absorbent structure exhibits, with regard to liquid drainage ability and liquid retention ability. By means of the possibility to vary the pattern structure, the fibre type and the type of carrier layer within the scope of the invention, however, a liquid-pervious cover layer is achieved, exhibiting a reduced surface wetness and an increased softness.
- The invention also includes an absorbent article such as a sanitary napkin, a panty-liner, a diaper, or the like comprising an absorbent body enclosed in a cover, wherein at least a portion of the cover consists of a liquid-

pervious cover layer in accordance with the invention. The liquid-pervious cover layer comprises a liquid-pervious carrier layer against which individual hydrophobic fibres, detached from each other and each exhibiting two fibre ends, are attached with one fibre end against the carrier layer. Thereby, an attachment angle α is formed between the carrier layer and each individual fibre. The liquid-pervious cover layer is primarily characterized in that the carrier layer exhibits a plurality of regions which are substantially free from fibres and which each occupies a surface such that a circle having a diameter of 3 to 15 mm and preferably having a diameter of 3 to 10 mm can be accommodated within each fibre-free region.

Furthermore, the invention includes a method of manufacturing a cover layer for an absorbent article wherein individual fibres, each exhibiting a first fibre end and a second fibre end, are applied with the first fibre end against a carrier layer. At least at the first fibre end, the cross-sectional area of the fibres exhibits a first portion primarily consisting of a first component and a second portion primarily consisting of a second component, wherein at least the first component is fusible and exhibits a melting temperature at which the second component occurs in a solid state. Only the first component is caused to melt, either before or after the application of the fibres against the carrier layer. Thereafter, the temperature of the fibres is lowered below the melting temperature of the first component, whereby a solid connection between the fibres and the carrier layer is obtained. The advantage of attaching the fibres to the carrier layer by means of causing the first component to melt is that the need for an adhesive when attaching the fibres to the carrier layer is eliminated. Furthermore, the need for a melted fibre fixation layer is eliminated, which

implies that the carrier layer can be constituted of a single material layer.

BRIEF DESCRIPTION OF THE DRAWINGS:

5

In the following, the invention will be described in greater detail with reference to the figures which are shown in the attached drawings.

10 Fig. 1 shows a cross-section through a liquid-pervious cover layer according to the invention;

Fig. 2 shows another cross-section through a liquid-pervious cover layer according to the invention and
15

Fig. 3 shows a sanitary napkin according to the invention seen from the side which is intended to be facing the user during use.
20

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS:

The liquid-pervious cover layer 1, shown in Fig. 1, consists of a carrier layer 2 onto which individual fibres
25 3 are attached. The individual fibres 3 are attached to the carrier layer 2 with one end, whereas the other, free end is directed away from the carrier layer, whereby the individual fibres are arranged at an angle α to the carrier layer. In the shown example, the attachment angle α is
30 approximately 90°, but may of course vary somewhat between the different fibres. In order to facilitate liquid passage through the liquid-pervious cover layer 1, the fibres 3 are arranged in spaced-apart regions with fibre-free regions 4 therebetween.

35

When attaching the fibres 3 to the carrier material 2, the fibres 3 are oriented so that one of the fibre ends is directed towards the carrier layer 2. This fibre orientation is achieved, for instance, by means of flocking. The individual fibres 3 are constituted of fibres comprising a surface which in the main is hydrophobic. Accordingly, the cover structure is constituted of for example a polyolefin. According to one embodiment, the fibres 3 are constituted of bicomponent fibres where the surface component consists of polyethylene, such as for example LDE (low density polyethylene), HDPE (high density polyethylene) or LLDPE (linear low density polyethylene). The fibre surface may further consist of polymeric mixtures comprising at least two of the above-mentioned polyethylene components, or other components exhibiting a substantially hydrophobic surface.

The core of the fibres 3 is constituted of a less hydrophobic material than the surface of the fibres. One example of a material which is less hydrophobic than polyethylene is polyester. Besides the fact that the component is less hydrophobic, polyester also exhibits a higher melting temperature than polyethylene. This difference in melting temperature between the components can be utilized when attaching the fibres to the carrier layer.

Since the fibres are heated to a temperature which is between the melting temperature of the two components during the attachment, a melted surface is formed on the bicomponent fibres, whereas the core remains solid. Thereby, the melted surface component may be utilized for attaching the fibres to the carrier layer 2, resulting in the elimination of the need for a special adhesive for the attachment of the fibres 3 to the carrier layer 2.

The attachment of the fibres 3 to the carrier layer 2 may of course also be accomplished with another attachment method. The bicomponent fibre may further consist of other components than those mentioned above which exhibit a difference in hydrophilicity. The individual fibres 3 can further be constituted of hollow fibres which exhibit a hydrophobic surface and a hollow core. The fibre surface may for example be constituted of polyolefins or other materials exhibiting a hydrophobic surface.

10

The carrier layer 2 may be a single material layer, or consist of a multilayered laminate. The carrier layer 2 shown in Fig. 1 may be constituted of a single material layer, such as for example a plastic film or a hydrophilic nonwoven.

15

The individual fibres 3 are attached to the carrier layer 2, for example by means of being applied onto a melted fibre fixation layer, or with an adhesive such as for example hot-melt, hydrophilic glue or any other adhesive which is suitable for the purpose. As mentioned above, the fibres 3 may further be attached to the carrier layer by means of the fibres 3 being constituted of bicomponent fibres comprising components exhibiting different melting temperatures. The fibres 3 may also be attached to the carrier layer by means of the fibres 3 being constituted of bicomponent fibres, comprising components exhibiting different melting temperatures. The fibres 3 may also be attached to the carrier layer 2 by means of the carrier layer 2 consisting of a multilayered laminate comprising a bottom layer and a fibre fixation layer. The bottom layer exhibits a higher melting temperature than the fibre fixation layer and consists of, for example, HDPE, polypropylene or another material suitable for the purpose.

The fibre fixation layer consists of for example LDPE, LLDPE, or other materials suitable for the purpose

35

exhibiting a lower melting temperature than the bottom layer material.

5 The liquid-pervious cover layer 201 shown in Fig. 2 has a similar construction as the liquid-pervious layer 1 shown in Fig. 1. Accordingly, the liquid-pervious layer 201 exhibits a barrier layer 202, such as the carrier layer 2 shown in Fig. 1, onto which fibres 203 are attached. The fibres 203 are attached to limited regions of the total
10 area of the carrier layer 202, whereby the carrier layer 202 exhibits regions which are free from fibres 203. The fibres 203 are attached with one of their ends, whereas the other, free end is directed away from the carrier layer 202, whereby the individual fibres 203 are attached at an
15 angle α to the carrier layer 202. The angle α between the individual fibres 203 and the carrier layer 202 is 30-70°, preferably approximately 45°. Since the individual fibres are angled to the carrier layer 202 with an angle α which is smaller than 90°, this implies that the regions of the
20 carrier layer 202 which are free from fibres 3 are not visible when the liquid-pervious layer 201 is observed from above.

25 Like the fibres 3, the fibres 203 may be constituted of bicomponent fibres or hollow fibres exhibiting a hydrophobic surface. The carrier layer 202 may be a single material layer, or consist of a multilayered laminate. The carrier layer 202 shown in Fig. 2 is only constituted of one layer, such as for example a plastic film or a
30 hydrophilic nonwoven. The fibres 203 are attached to the carrier layer 202 for example by means of being applied onto a melted fibre fixation layer, or by means of being applied onto an adhesive layer such as for example hot-melt, hydrophilic glue or any other adhesive suitable for
35 the purpose. Furthermore, the fibres 203 may be constituted of bicomponent fibres consisting of a fibre

surface with a lower melting temperature than the core of the bicomponent fibres. This implies that the melted surface component of the fibres 203 attaches to the carrier surface and consequently the need for a special adhesive is eliminated.

The sanitary napkin 300 shown in Fig. 3 comprises a liquid-pervious cover layer 301 according to the invention, a liquid-impervious cover layer 305, and an absorbent body 306 enclosed between the cover layers. The liquid-impervious cover layer 305 comprises a plastic film, a hydrophobicated fibre fabric, a laminate of these materials, or any other similar material suitable for the use, placed on the side of the sanitary napkin which is intended to be facing away from the user during use.

The absorbent body 306 enclosed between the cover layers 301, 305 is usually composed of one or several layers of cellulose fluff pulp. The cellulose fluff pulp may be blended with fibres or particles of a highly absorbent polymeric material of the type which during absorption chemically binds large quantities of liquid while forming a liquid-containing gel. In order to improve the properties of the absorbent body 306, additional components may further be included in the absorbent body. Examples of such components are binder fibres, shape-stabilizing components, or the like. Furthermore, the absorbent body 306 can be constituted of absorbent foams, or of any other liquid-absorbent material.

The cover layers 301, 305 have a larger extension in the plane of the sanitary napkin 300 than the absorbent body 306, around the entire periphery of this. The projecting portions 308 of the cover layers 301, 305 are mutually connected around the absorbent body 306, for example by means of gluing, welding, or in another way.

The liquid-pervious cover layer 301 has a similar construction to the liquid-pervious cover layer 1 shown in Fig. 1 and, accordingly, exhibits a carrier layer 302, to which fibres 303 are attached in a surface pattern of stripes or band-shaped regions alternating with fibre-free, or essentially fibre-free band-shaped regions 304. The width of the fibre-free regions 4 should be in the order of 3-15 mm and preferably 3-10 mm.

10 The fibres 303 are attached to the carrier layer 302 with an attachment angle α which is approximately 90° , but which of course may vary somewhat between the different fibres. The cover layer 301 is liquid-pervious since the carrier layer 302 exhibits perforations through the material, or by means of the carrier layer being constituted of a liquid-pervious material such as for example a hydrophilic nonwoven. Furthermore, the absorbent body 306 can constitute a carrier layer 302, when it exhibits a sufficient cohesive ability, wherein the fibres are attached directly to the side of the absorbent structure which is intended to bear against the user during use.

25 In the preceding embodiments, the invention has been described with reference to sanitary napkins but is, as already mentioned, of course also applicable to incontinence protectors, diapers, panty-liners and the like.

30 The invention further relates to all conceivable combinations of the above-mentioned embodiments, and is also applicable for other embodiments within the scope of the following claims.

5

CLAIMS:

10

1. A liquid pervious cover layer (1) for an absorbent article such as a diaper, an incontinence protector, a sanitary napkin (300) or the like, which exhibits a liquid-pervious carrier layer (2) having a first surface and a second surface, wherein the first surface of the carrier layer (2) exhibits a multitude of individually arranged fibres (3), each fibre exhibiting a first fibre end and a second fibre end, and being attached with one fibre end against the first surface of the carrier layer (2),
c h a r a c t e r i z e d i n that the carrier layer (2) exhibits a plurality of regions (4) which are substantially free from fibres (3) and which each occupies a surface such that a circle having a diameter of 3 to 15 mm and preferably having a diameter of 3 to 10 mm can be accommodated within each fibre-free region (4).

2. A liquid-pervious cover layer according to claim 1 , c h a r a c t e r i z e d i n that the individual fibres (3) are constituted of bicomponent fibres exhibiting a fibre surface and a core, wherein at least the fibre surface is hydrophobic.

3. A liquid-pervious cover layer according to claim 2, c h a r a c t e r i z e d i n that the fibre surface is more hydrophobic than the core.

4. A liquid-pervious cover layer according to claim 2,

c h a r a c t e r i z e d i n t h a t t h e f i b r e s u r f a c e
exhibits a lower melting temperature than the core.

5 5. A liquid-pervious cover layer according to claim 1,
c h a r a c t e r i z e d i n t h a t t h e f i b r e s (3) a r e
constituted of hollow fibres having an outer surface and an
inner surface, whereof at least the outer surface is
hydrophobic.

10 6. A liquid-pervious cover layer according to any one of
claims 1-5, c h a r a c t e r i z e d i n t h a t t h e f i b r e s
(3) a r e a t t a c h e d t o t h e f i r s t s u r f a c e o f t h e c a r r i e r l a y e r
(2) w i t h a n a t t a c h m e n t a n g l e α b e t w e e n t h e c a r r i e r l a y e r
(2) a n d e a c h i n d i v i d u a l f i b r e (3) b e i n g 30-90°.

15 7. A liquid-pervious cover layer according to any one of
the preceding claims, c h a r a c t e r i z e d i n t h a t
the carrier layer (2) i s c o n s t i t u t e d o f a m u l t i l a y e r e d
laminate.

20 8. A liquid-pervious cover layer according to any one of
the preceding claims, c h a r a c t e r i z e d i n t h a t
the carrier layer (2) c o m p r i s e s a p e r f o r a t e d p l a s t i c f i l m .

25 9. A liquid-pervious cover layer according to any one of
the preceding claims, c h a r a c t e r i z e d i n t h a t
the carrier layer (2) c o m p r i s e s a h y d r o p h i l i c n o n w o v e n .

30 10. A liquid-pervious cover layer according to any one of
the previous claims, c h a r a c t e r i z e d i n t h a t
the carrier layer (2) , w i t h i n d i f f e r e n t r e g i o n s o f t h e
surface of the carrier layer (2) , e x h i b i t s a d i f f e r e n c e i n
the number of attached individual fibres (3) p e r u n i t o f
area.

35 11. A liquid-pervious cover layer according to any one of
the preceding claims, c h a r a c t e r i z e d i n t h a t

the hydrophobic fibres (3) are 0.3-2.5 mm long and preferably 0.3-1.5 mm long.

5 12. A liquid-pervious cover layer according to any one of the preceding claims, characterized in that the carrier layer (302) exhibits a plurality of fibres (303) arranged in band-shaped regions (304) on the first surface of the carrier layer (302), the distance between two neighbouring fibre-covered regions being 3-15 mm and
10 preferably 3-10 mm.

13. A liquid-pervious cover layer according to any one of the preceding claims, characterized in that the fibre-free regions (4) occupy at least 25% of the
15 surface of the carrier layer (2).

14. An absorbent article such as a diaper, an incontinence protector, a sanitary napkin (300) or the like, comprising an absorbent body (306) enclosed in a cover, wherein at
20 least a portion of the cover consists of a liquid-pervious cover layer (301) according to claim 1 comprising a carrier layer (302) against which individual hydrophobic fibres (303), detached from each other and each exhibiting two fibre ends, are attached with one fibre end against the
25 carrier layer (302) with an attachment angle α between the carrier layer (302) and each individual fibre (303), characterized in that the carrier layer (302) exhibits a plurality of regions (304) which are substantially free from fibres (303) and which each
30 occupies a surface such that a circle having a diameter of 3 to 15 mm and preferably having a diameter of 3 to 10 mm can be accommodated within each fibre-free region (304) of the carrier layer (302).

35 15. A method of manufacturing a cover layer (1) according to claim 1 for an absorbent article wherein individual

fibres each exhibiting a first fibre end and a second fibre end are applied with the first fibre end against a carrier layer (2),

5 c h a r a c t e r i z e d i n that the fibres (3), at least at the first fibre end, in cross-section exhibits a first portion primarily consisting of a first component, and a second portion primarily consisting of a second component, wherein at least the first component is fusible and exhibits a melting temperature at which the second

10 component occurs in a solid state, wherein only the first component is caused to melt, at least at the first fibre end of the fibres, whereby the fibres (3) attach to the carrier layer (2), whereafter the temperature of the fibres (3) is lowered to a temperature below the melting

15 temperature of the first component, whereby a solid connection between the fibres (3) and the carrier layer (2) is obtained.

1/2




FIG. 1





FIG. 2

2/2

FIG. 3

INTERNATIONAL SEARCH REPORT

International application No.
PCT/SE 98/00292

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: A61F 13/15, A61F 13/46
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, EDOC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0737462 A1 (PANTEX S.R.L.), 16 October 1996 (16.10.96), column 3, line 43 - line 51, figure 5, abstract --	1,2,4-14
Y	WO 9700656 A1 (THE PROCTER & GAMBLE COMPANY), 9 January 1997 (09.01.97), page 5, line 30 - page 7, line 32, figures 1,2, abstract --	1,2,4-14
A	BE 1007041 A5 (FILIPOVIC' DRAGOMIR), 28 February 1995 (28.02.95), claims 3,6 --	1-15

☒ Further documents are listed in the continuation of Box C. ☒ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"B" earlier document but published on or after the international filing date	"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 3 June 1998	Date of mailing of the international search report 16 -06- 1998
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86	Authorized officer Tommy Somlo Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 98/00292

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3967623 A (GEORGE A.M. BUTTERWORTH ET AL), 6 July 1976 (06.07.76), column 3, line 33 - line 39 ----- -----	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/SE 98/00292

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0737462 A1	16/10/96	NONE	
WO 9700656 A1	09/01/97	AU 6049296 A EP 0833598 A	22/01/97 08/04/98
BE 1007041 A5	28/02/95	NONE	
US 3967623 A	06/07/76	NONE	